




VIS POLYESTER VIS/V

PLASTOMERIC DISTILLED POLYMER-BITUMEN WATERPROOFING
MEMBRANES, BASED ON DISTILLED BITUMEN AND PLASTOMERS

GRANTS *LEED* CREDITS

CATEGORY	CHARACTERISTICS		ENVIRONMENTAL									METHOD OF USE		
		 Reazione al fuoco												
PLASTOMERIC	WATERPROOF	REACTION TO FIRE	ECO GREEN	ASBESTOS FREE	TAR FREE	CHLORINE FREE	RECYCLABLE	NON DANGEROUS	EXHAUSTED OIL FREE	TORCH APPLICATION	HOT AIR APPLICATION	NAILING		

DESCRIPTION

The **VIS** membranes are made up of distilled bitumen, selected for industrial use, with elastomeric and plastomeric polymers added to obtain a "phase inversion compound" whose continuous phase is formed by polymers in which the bitumen is dispersed, where the characteristics are determined by the polymeric matrix and not by the bitumen even though this is the most consistent ingredient.

The performance of the bitumen is therefore increased along with the durability and the resistance to high and low temperatures while the already optimum adhesive and waterproofing qualities of the bitumen remain unchanged. **VIS** is produced in various weights and reinforced with fibreglass mat and in stabilized "non woven" polyester fabric.

VIS POLYESTER is reinforced with a rot-proof "non woven" polyester fabric composite, stabilized with fibreglass mat which is very strong and elastic with optimal dimensional stability in hot conditions which reduces the problems of the straightness and the retraction of head lap joints as it is 2 to 3 times more stable than normal reinforcements in "non woven" polyester fabric.

VIS/V is reinforced with rot-proof fibreglass mat which is strengthened longitudinally and has high dimensional stability properties.

The **VIS** membranes have the upper face of the membrane coated with a uniformly distributed, fine serigraphed talc, a patented treatment which makes it possible to quickly unroll the rolls and install the membranes with the reliable and fast welding of the joints.

The underside of the membrane is coated with Flamina, a plastic film that melts when torched and which is embossed both to obtain the pre-tension and therefore the optimal retraction of the film and also to offer the torch a greater surface area for faster and more reliable installation.

When the membrane is dry laid or spot bonded, the embossing diffuses the vapour.

APPLICATION FIELDS

The long lasting strength, elasticity and stability at high and low temperatures make **VIS POLYESTER** membrane ideal for use in non cold climates, as a single or multi-layer waterproofing systems for new building work or for refurbishment:

- **On all sloping surfaces:** on flat, vertical and curved surfaces.
- **On different types of substrates:** site-cast or prefabricated concrete substrates, on timber roofing, on the most common thermal insulation used in the building trade.

CE

INTENDED USE OF "CE" MARKING SPECIFIED ACCORDING TO THE AISPEC-MBP GUIDLINES

EN 13707 - REINFORCED BITUMEN SHEETS FOR ROOF WATERPROOFING

- Under layer or intermediate layer in multi-layer systems without permanent heavy surface protection
- VIS POLYESTER
- VIS/V

EN 13969 - BITUMEN DAMP PROOF SHEET INCLUDING BITUMEN BASEMENT TANKING SHEETS

- Membranes for foundations
- VIS POLYESTER


TECHNICAL CHARACTERISTICS

	Standard	T	VIS POLYESTER				VIS/V		
Reinforcement			“Non-woven” composite polyester stabilized with fibreglass				Fibreglass		
Thickness	EN 1849-1	±0,2	3 mm	4 mm	–	–	–	–	–
Mass per unit area	EN 1849-1	±10%	–	–	3 kg/m²	4 kg/m²	2 kg/m²	3 kg/m²	4 kg/m²
Roll size	EN 1848-1	–1%	1×10 m	1×10 m	1×10 m	1×10 m	1×10 m	1×10 m	1×10 m
Watertightness • after ageing	EN 1928 – B EN 1926-1928	≥ ≥	60 kPa 60 kPa				60 kPa –		
Shear resistance	EN 12317-1	–20%	350/250 N/50mm				350/250 N/50mm		
Maximum tensile force L/T	EN 12311-1	–20%	400/300 N/50 mm				300/200 N/50 mm		
Elongation L/T	EN 12311-1	–15% V.A.	35/40%				2/2%		
Resistance to impact	EN 12691 – A		700 mm				–		
Resistance to static loading	EN 12730 - A		10 kg				–		
Resistance to tearing (nail shank) L/T	EN 12310-1	–30%	140/140 N				70/70 N		
Flexibility to low temperature	EN 1109	≤	0°C				0°C		
Flow resist. at high temp. • after ageing	EN 1110 EN 1296-1928	≥	110°C 100°C				110°C 100°C		
Reaction to fire Euroclass	EN 13501-1		E				E		
External fire performance	EN 13501-5		F roof				F roof		
Thermal specifications									
Thermal conductivity			0.2 W/mK	0.2 W/mK	0.2 W/mK	0.2 W/mK	0.2 W/mK	0.2 W/mK	0.2 W/mK
Heat capacity			3.90 KJ/K	5.20 KJ/K	3.60 KJ/K	4.80 KJ/K	2.40 KJ/K	3.60 KJ/K	4.80 KJ/K


Compliant with EN 13707 in terms of the resistance factor to steam penetration for reinforced polymer-bitumen membranes, the value of $\mu = 20\,000$ may be considered, unless declared otherwise.

COMPOSITION OF THE MEMBRANE

VIS POLYESTER



VIS/V



PRODUCT FINISHING



EMBOSSING FLAMINA. The embossing on the lower surfaces of the membranes finished with Flamina film makes it possible to lay the product precisely and quickly, forming a smooth surface when melted with the torch. It indicates the correct melting temperature and lets the film retract faster. The embossing also enables optimal vapour diffusion; in spot bonded and loose laid installation, in the points where it remains intact, preventing blisters and swelling.



TALC SURFACING. The talcing of the top face is carried out with a technique which evenly spreads the very thin talc over the top surface with a special pattern, preventing accumulation or zones without talc. This new system allow a quick unroll and gives the surface a pleasant aspect, which enable to torch it faster if compared to the other coarser mineral finishes.

• FOR ANY FURTHER INFORMATION OR ADVICE ON PARTICULAR APPLICATIONS, CONTACT OUR TECHNICAL OFFICE • IN ORDER TO CORRECTLY USE OUR PRODUCTS, REFER TO INDEX TECHNICAL SPECIFICATIONS •

index
Construction Systems and Products

Via G. Rossini, 22 - 37060 Castel D'Azzano (VR) - Italy - C.P.67
T. +39 045 8546201 - F. +39 045 518390

Internet: www.index-spa.com
Informazioni Tecniche Commerciali
tecom@indexspa.it
Amministrazione e Segreteria
index@indexspa.it
Index Export Dept.
index.export@indexspa.it



the numerous possible uses and the possible interference of conditions or elements beyond our control, we assume no responsibility regarding the results which are obtained. The purchasers, of their own accord and under their own responsibility, must establish the suitability of the product for the envisaged use.

The figures shown are average indicative figures relevant to current production and may be changed or updated by INDEX at any time without previous warning. The advice and technical information provided, is what results from our best knowledge regarding the properties and the use of the product. Considering